













Caratteristiche tecniche Technical sheet

FATTO A MANO / HANDMADE

TECHNICAL SHEET	NORMS	EN-NORM VALUES	MANETTI VALUES
 surface quality	UNI EN 98	percentage of acceptable tiles in the lot free visible defects 95 min	corresponding
 water absorption	ISO 10545-3		7,3
 modulus of ropture	UNI EN 100	average value >10N/mm ²	> 20 N/mm ²
 scratch hardness of surface (Mohs)	UNI EN 101	unglazed tiles 5 min	5
 abrasion resistance	ISO 10545-6		1116 mm ³
 resistance to light	DIN 51094	free of visible defects	resistant
 linear thermal expansion	ISO 10545-8	coefficient linear thermal expansion from ambient temperature $10^{-6}/^{\circ}\text{C}^{-1}$	7,0(x10 ⁻⁶ /°C ⁻¹)
 thermal shock resistance	UNI EN 104 ASTM/C 484	free of visible defects	resistant
 res. to household chemical swimming pool water cleaners	ISO 10545	free of visible defects	resistant
 resistance to acid and alkalis	ISO 10545-13	unglazed tiles	resistant
 frost resistance	ISO 10545-12	free of visible defects	resistant
 sliding resistance	DM 236/86 DIN 51130	leather on dry surface $\mu > 0,40$ test on inclined lan	R13 R12 (Vellutato rosato, Vellutato giallo Capalbio, Terre colorate) R10 (Fatto a mano levigato, Fatto a mano anticato)

TERRA
COTTA